



**NYLON-6 BCF TEXTURIZED CARPET YARN PRODUCED AT
“MICROFILM” MACHINE.**

BCF texturized yarn is intended for production of tufting floor coverings, upholstery and other articles.

Nominal Linear Density, dtex	Count of Filaments	Tenacity , gf/tex, min	Elongation at break, %, max	Yarn tensility, %	Number of entangling points per 1m of yarn	Remarks
1300x1	68	21.7	55.0	5.0 – 11.5	10 – 30	bright, of profile cross section- “trilobal”; undyed, spundyed, untistatcal
Actual humidity, %, max	Bobbin type	Bobbin weight, g	Actual humidity, %, max	Tube dimensions, mm, L/Ø	Bean diameter, mm, max	
7.0	cylindrical	4280±50	7.0	292/75	280	

Bobbins are placed onto pallets forming block-packs. Each block-packed is stretch-foiled.