



NYLON-66 INDUSTRIAL FILLAMENT.

No	Item	930 dtex (840 D)	1400 dtex (1260D)	1870 dtex (1680D)	2100 dtex (1890D)
1	Filament #	140	208	280	312
2	Linear Density (dtex)	930±17	1400±23	1870±33	2100±39
3	Breaking Strength (N)	78.0	117.2	156.4	176.5
4	Elongation at Load (%)	12±1.5 44.1N	12±1.5 66.6N	12±1.5 88.2N	12±1.5 100.0N
5	Elongation at Break (%)	19±3	19±3	19±3	19±3
6	Heat Stability (%) (dry air 180 4 hrs)	90	90	90	90
7	Shrinkage in Boiling Water for 30 min (%)	7±2	7±2	7±2	7±2

Remark: The above are specifications of normal products; it can be adjusted according to client's special needs.